

Schooner Tropical

Varnishes

Interior/Exterior Clear Gloss Finish on Timber



PRODUCT DESCRIPTION

A classic very high gloss marine grade varnish. Specifically formulated for use where tropical exposure will occur.

- * Excellent flow and brushability
- * Excellent resistance to severe tropical exposure conditions
- * Contains special UV absorbers to further help prevent cracking and loss of gloss

PRODUCT INFORMATION

Colour	YVA088-Red /Brown Transparent when cured
Finish	Very High Gloss
Specific Gravity	0.9
Volume Solids	46%
Typical Shelf Life	2 yrs
VOC (As Supplied)	437 g/lit
Unit Size	500 ml , 1 Lt , 4 Lt

DRYING/OVERCOATING INFORMATION

	Drying							
	10°C (50°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Touch Dry	18 hrs		11 hrs		6 hrs		3 hrs	

	Overcoating							
	Substrate Temperature							
	10°C (50°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Goldspar Original	2 days	5 days	40 hrs	4 days	18 hrs	2 days	12 hrs	1 days
Goldspar Satin	2 days	5 days	40 hrs	4 days	18 hrs	2 days	12 hrs	1 days
Schooner Tropical	2 days	5 days	40 hrs	4 days	18 hrs	2 days	12 hrs	1 days

Note: If Maximum Recoat Times are exceeded, sand using 320-400 grade (grit) wet or dry paper.

APPLICATION AND USE

Preparation	All surfaces to be coated should be clean, dry and free from contamination.
Hints	<p>Thinner YTA800 International Enamel Thinners #1. Thin up to 30% as required when spraying.</p> <p>Cleaner YTA800 International Enamel Thinners #1.</p> <p>Ventilation and Humidity Control Ensure adequate ventilation during use.</p> <p>Airless Spray Pressure: 176-210 bar. Tip Size: 1365-1580.</p> <p>Conventional Spray Pressure: 2.3 bar. Tip size: 1.1-1.3 mm.</p> <p>Other For Airmix spray application: Pressure: 2.0 bar. Tip Size: 06-113.</p>
Some Important Points	Do not use straight from can otherwise contents will age prematurely. Product temperature should be minimum 15°C/60°F and maximum 30°C/86°F. Ambient temperature should be minimum 10°C/50°F and maximum 35°C/95°F. Substrate temperature should be minimum 10°C/50°F and maximum 35°C/95°F.
Compatibility/Substrates	Suitable for Timber above the Waterline. May be applied after thinning, to naturally oily timbers such as Teak and Iroko after suitable degreasing.
Number of Coats	6 minimum for temperate and 10 minimum for semi-tropical/tropical exterior. 3 minimum for interior.
Coverage	(Theoretical) - 20 m ² /lit
Recommended DFT per coat	23 microns dry
Recommended WFT per coat	50 microns wet
Application Methods	Airless Spray, Brush, Conventional Spray, Airmix, Roller

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	<p>TRANSPORTATION:</p> <p>Schooner Tropical should be kept in securely closed containers during transport and storage.</p> <p>STORAGE:</p>
----------------	--

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.

Schooner Tropical

Varnishes

Interior/Exterior Clear Gloss Finish on Timber



Exposure to air and extremes of temperature should be avoided. For the full shelf life of Schooner Tropical to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.

Safety

DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line. Always use gloves and goggles and keep skin protected with overalls. Users should ensure they have a copy of the Material Safety Datasheet for this product and that they are familiar with all the safety directions before use.

IMPORTANT NOTES

The technical information and suggestions for use and application presented herein are not intended to be exhaustive, but they represent the best information available to use and are believed to be reliable. They should not, however, be construed as controlling suggestions and there is no warranty of performance of our materials either expressed or implied. We urge that users of our materials conduct confirmatory tests to determine final suitability for their specific end uses. Because this datasheet is subject to changes from time to time, it is the user's responsibility to check that this sheet is current prior to using the product.

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.