

# Interdeck

## Finishes

### Slip Resistant Deck Paint



#### PRODUCT DESCRIPTION

Interdeck provides an excellent slip resistant finish. It contains a fine aggregate and will apply easily on all substrates.

\* Low sheen finish prevents dazzling reflected sunlight off decks

\* Easy application

\* Available in a range of colours

The tough polyurethane resin protects decks against everyday wear and tear.

#### PRODUCT INFORMATION

<b>Colour</b>	YJB000-White, YJB923-Squall Blue, YJC089-Cream, YJF684-Grey
<b>Finish</b>	Low sheen
<b>Specific Gravity</b>	1.4
<b>Volume Solids</b>	54%
<b>Typical Shelf Life</b>	2 yrs
<b>VOC (As Supplied)</b>	357 g/lit
<b>Unit Size</b>	500 ml (white only), 1 lt, 4 lt (white only)

#### DRYING/OVERCOATING INFORMATION

	Drying							
	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Dry To Walk On	4 days		3 days		2 days		1 days	
Touch Dry	5 hrs		4 hrs		3 hrs		2 hrs	

  

	Overcoating							
	Substrate Temperature							
	5°C (41°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Overcoated By	Min	Max	Min	Max	Min	Max	Min	Max
Interdeck	24 hrs	4 days	20 hrs	3 days	16 hrs	2 days	12 hrs	1 days

#### APPLICATION AND USE

##### Preparation

##### PREVIOUSLY PAINTED SURFACES

**In Good Condition** Wash down with a suitable detergent, rinse with fresh water and allow to dry. Abrade with 280-320 grade (grit) paper. Apply one coat of Pre-Kote all over followed by 1-2 coats of Interdeck. In Poor Condition Remove all previous coatings and prime the substrate.

**TIMBER** Sand smooth with 80-180 grade paper and then 280 grade paper. Remove sanding dust by brushing, dusting and wiping. If wiping with solvent then allow to dry completely before applying primer. Prime with Yacht Primer.

**STEEL** Degrease with solvent. Gritblast to Sa 2½ - near white metal surface. If gritblasting is not possible, grind the metal surface with 24-36 grit abrasive discs to a uniform, clean, bright metal surface with a 50-75 microns anchor pattern. Use angle grinder on small areas. Clean thoroughly and allow to dry. Prime with Yacht Primer or Interprotect.

**ALUMINIUM** Degrease with solvent or Super Cleaner. Sand well using 24-120 grade (aluminium compatible) paper. Coarser grades are recommended to achieve optimum adhesion. Clean thoroughly and allow to dry. Prime with Yacht Primer as soon as possible (within 8 hours).

**GRP** In new or excellent condition Degrease with solvent or Super Cleaner. Sand well using 180-220 grade paper. Clean thoroughly and allow to dry. No primer required - apply Pre-Kote direct to GRP.

**AGED/WEATHERED GELCOATS** Due to the potentially porous nature of aged/weathered gelcoats the risk of solvent/moisture entrapment after painting is much higher than when gelcoat is new. As a result this entrapment could lead to blistering of the paint film. To reduce the risk of paint film blistering it is recommended that 3 coats of Interprotect are applied to seal the gelcoat. Interprotect must be overcoated with Perfection Undercoat prior to topcoat application.

**ALL SUBSTRATES** Use Pre-Kote undercoat.

##### Method

Sand the undercoat with 180-220 grade wet or dry paper. Remove dust with a dust wipe. Apply 1-2 coats.

##### Hints

**Mixing** Stir well before use.

**Thinner** YTA800 International Enamel Thinners #1.

**Thinning** Thinning is not recommended.

**Cleaner** YTA800 International Enamel Thinners #1.

**Ventilation and Humidity Control** Apply in dry, well ventilated conditions.

**Other** For best results either stipple by brush or use a mohair roller.

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.

# Interdeck

## Finishes

### Slip Resistant Deck Paint



<b>Some Important Points</b>	Product temperature should be minimum 10°C and maximum 30°C. Ambient temperature should be minimum 5°C/41°F and maximum 35°C/95°F. Substrate temperature should be minimum 5°C/41°F and maximum 35°C/95°F.
<b>Compatibility/Substrates</b>	Suitable for all substrates and filled surfaces. Not suitable for permanently immersed surfaces. Do not clean with highly alkaline cleaners.
<b>Number of Coats</b>	1-2
<b>Coverage</b>	(Theoretical) - 10.8 m <sup>2</sup> /lt (Practical) - 9.7 m <sup>2</sup> /lt
<b>Recommended DFT per coat</b>	50 microns dry
<b>Recommended WFT per coat</b>	93 microns wet
<b>Application Methods</b>	Brush, Roller

#### TRANSPORTATION, STORAGE AND SAFETY INFORMATION

<b>Storage</b>	<b>TRANSPORTATION:</b> Interdeck should be kept in securely closed containers during transport and storage. <b>STORAGE:</b> Exposure to air and extremes of temperature should be avoided. For the full shelf life of Interdeck to be realised ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.
<b>Safety</b>	<b>DISPOSAL:</b> Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal. <b>GENERAL:</b> Read the label safety section for Health and Safety Information, also available from our Technical Help Line. Always use gloves and goggles and keep skin protected with overalls. Users should ensure they have a copy of the Material Safety Datasheet for this product and that they are familiar with all the safety directions before use.
<b>IMPORTANT NOTES</b>	<i>The technical information and suggestions for use and application presented herein are not intended to be exhaustive, but they represent the best information available to use and are believed to be reliable. They should not, however, be construed as controlling suggestions and there is no warranty of performance of our materials either expressed or implied. We urge that users of our materials conduct confirmatory tests to determine final suitability for their specific end uses. Because this datasheet is subject to changes from time to time, it is the user's responsibility to check that this sheet is current prior to using the product.</i>

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.