

Goldspar Original

Varnishes

Interior/Exterior Clear Gloss Finish on Timber



PRODUCT DESCRIPTION

An original premium interior/exterior modified alkyd marine varnish.

- * Can be applied by brush, roller or spray
- * Tough, durable cured film
- * Excellent UV protection

PRODUCT INFORMATION

Colour	YVA210 Cured film is clear light amber.
Finish	High Gloss
Specific Gravity	0.9
Volume Solids	46%
Typical Shelf Life	2 yrs
VOC (As Supplied)	437 g/lit
Unit Size	250 ml 500 ml 1 Lt 2 Lt

DRYING/OVERCOATING INFORMATION

	Drying							
	10°C (50°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
Touch Dry	15 hrs		10 hrs		5 hrs		3 hrs	
	Overcoating							
	Substrate Temperature							
Overcoated By	10°C (50°F)		15°C (59°F)		23°C (73°F)		35°C (95°F)	
	Min	Max	Min	Max	Min	Max	Min	Max
Goldspar Original	40 hrs	5 days	32 hrs	4 days	16 hrs	2 days	8 hrs	1 days
Goldspar Satin	40 hrs	5 days	32 hrs	4 days	16 hrs	2 days	8 hrs	1 days
Schooner Tropical	40 hrs	5 days	32 hrs	4 days	16 hrs	2 days	8 hrs	1 days

Note: If Maximum Recoat Times are exceeded, sand using 320-400 grade (grit) wet or dry paper.

APPLICATION AND USE

Preparation	All surfaces to be coated should be clean, dry and free from contamination.
Hints	<p>Thinner YTA800 International Enamel Thinners #1. Thin up to 30% as required when spraying.</p> <p>Cleaner YTA800 International Enamel Thinners #1.</p> <p>Ventilation and Humidity Control Ensure adequate ventilation during use.</p> <p>Airless Spray Pressure: 176-210 bar. Tip Size: 1365-1580.</p> <p>Conventional Spray Pressure: 2.3 bar. Tip size: 1.1-1.3 mm.</p> <p>Other For Airmix spray application: Pressure: 2.0 bar. Tip Size: 06-113.</p>
Some Important Points	Product temperature should be minimum 15°C/60°F and maximum 30°C/86°F. Ambient temperature should be minimum 10°C/50°F and maximum 35°C/95°F. Substrate temperature should be minimum 10°C/50°F and maximum 35°C/95°F.
Compatibility/Substrates	Suitable for Timber above the Waterline. May be applied after thinning, to naturally oily timbers such as Teak and Iroko after suitable degreasing.
Number of Coats	6 minimum for temperate and 10 minimum for semi-tropical/tropical exterior. 3 minimum for interior.
Coverage	(Theoretical) - 18 m ² /lt
Recommended DFT per coat	26 microns dry
Recommended WFT per coat	56 microns wet
Application Methods	Airless Spray, Brush, Conventional Spray, Airmix, Roller

TRANSPORTATION, STORAGE AND SAFETY INFORMATION

Storage	<p>TRANSPORTATION: Goldspar Original should be kept in securely closed containers during transport and storage.</p> <p>STORAGE: Exposure to air and extremes of temperature should be avoided. For the full shelf life of Goldspar Original to be realised</p>
----------------	--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.

Goldspar Original

Varnishes

Interior/Exterior Clear Gloss Finish on Timber



ensure that between use the container is firmly closed and the temperature is between 5°C/41°F and 35°C/95°F. Keep out of direct sunlight.

Safety

DISPOSAL: Do not discard tins or pour paint into water courses, use the facilities provided. It is best to allow paints to harden before disposal.

GENERAL: Read the label safety section for Health and Safety Information, also available from our Technical Help Line. Always use gloves and goggles and keep skin protected with overalls. Users should ensure they have a copy of the Material Safety Datasheet for this product and that they are familiar with all the safety directions before use.

IMPORTANT NOTES

The information given in this sheet is not intended to be exhaustive. Any person using the product without first making further written enquiries as to the suitability of the product for the intended purpose does so at their own risk and we can accept no responsibility for the performance of the product or for any loss or damage (other than death or personal injury resulting from negligence) arising out of such use. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

Please refer to your local representative or visit <http://www.yachtpaint.com> for further information.

All trademarks mentioned in this publication are owned by, or licensed to, the AkzoNobel group of companies. © AkzoNobel 2014.